


## Product Information



Baton Rouge Industries, LLC  
5319 Groom Rd · P.O. Box 26  
Baker, Louisiana 70714  
1-800-232-0334 · 225-775-3362  
Fax: 225-775-3498  
[BatonRougeIndustries.com](http://BatonRougeIndustries.com)

### M-24

## Lithium 12 Hydroxy Grease For Automatic Lube Systems

01/01/25

### Description

**M-24 Lithium 12 Hydroxy Greases** are outstanding multi-purpose, lithium 12 hydroxy greases. These high- quality greases are manufactured with superior quality base oils and are fortified with a synergistic combination of performance additives

**M-24 Lithium 12 Hydroxy Greases** have a customized formulation that provides superior anti-friction and film protection under heavy load conditions. These Greases are also water resistance and maintaining lubrication in long-life service. These greases offer excellent low temperature pumpability and high temperature protection.

### Product Features

- Lithium 12 hydroxy base
- Excellent thermal and oxidation stability
- Good pump ability at low temperatures
- Excellent for automatic lube systems

### Customer Benefits

- Superior lubrication under severe conditions
- Suitable for low temperature applications
- Better rust protection

### Applications

- Highly recommended for chassis, universal joints and wheel bearing applications
- Extended service life in heavy duty automotive, trucks, buses, and farm tractors
- Suitable for a wide range of industrial applications
- Excellent for automatic lube systems

<b>M-24 Lithium 12 Hydroxy Grease</b>		
<b>Product Number</b>	<b>M-24 Lithium 12 Hydroxy Grease</b>	<b>Test Method</b>
Color	Amber	Visual
Texture	Smooth	Visual
Thickener	Li-12-Hydroxy	-
NLGI Grade	2	ASTM D-217
Worked Penetration	265-295	ASTM D-217
Drop Point, °F	360 min	ASTM D-2265
Viscosity @ 40 °C, cSt	145	ASTM D-445
Viscosity @ 100 °C, cSt	10.6	ASTM D-445
Viscosity @ 100 °F, SUS	775	
Viscosity @ 210 °F, SUS	62.5	
Steel Mobility @ 0 °F	7.4 g/m	
@ -30 °F	0.1 g/m	
Weld Load, kg	225	ASTM D-2596
Timken OK, lbs	40	ASTM D-2509
Rust Protection	Pass	ASTM D-1743